

Rhenodiv® BO-501-2

Release Agents

Function

Compound release agent in powder form for batch-off operations

Product description

Composition:	combination of inorganic fillers, synthetic fillers and surfactants
Appearance:	grayish powder
Bulk density [g/cm ³ @20°C]:	ca. 0.62
Ash content [%]:	approx. 63
pH, 20 °C (5 %):	approx. 9.5
Solubility:	dispersible in water
Physiological properties:	see safety data sheet

Use

Mode of action: Rhenodiv BO-501-2 is a batch-off release agent for rubber processing (slab dip process). It is a powder (100 % of active ingredient). Rhenodiv BO-501-2 exhibits the following characteristics:

- easy to disperse in water
- compatible with water of different hardness
- excellent wetting of rubber sheets
- excellent release effect
- fast drying
- low working concentration, low consumption
- low dust formation
- low build-up and contamination of the equipment
- minimal sedimentation
- minimal foam formation

Rhenodiv BO-501-2 forms a thin, flexible film on the surface of the rubber sheets. The special inorganic fillers of optimized particle size distribution act as microscopic spacers between the sheets, providing excellent release properties. Still, friction between the sheets is sufficient to prevent sheets from slipping during storage, while allowing smooth, continuous feeding of extruders. Economic and efficient working is provided.

Processing: For best performance good dispersion of the powder in water is crucial. It is recommended to use a separate dispersion tank equipped with a paddle stirrer. The powder is added to the water that ideally has a temperature of ca. 50 °C. The slurry should be stirred for at least 30 min before use. Dispersion time in cold water should be extended as long as necessary. Optimal results are achieved by preparing a slurry of 10-12 % concentration in a first stage which will then be diluted to the actual work concentration. During the batch-off process only slight agitation is needed to prevent sedimentation. Usually the motion of the bath during to the dipping process is sufficient.

Dosage: Depending on the type of rubber compound, a working concentration of 1.5-3.0 % is recommended.

Applications: Standard slab dip equipment

Packing

20 kg paper bags on 800 kg plastic palettes

Storage stability

In original closed containers under cool and dry conditions 24 months min. from day of production

Handling

Please consult material safety data sheet (MSDS) for additional handling information on Rhenodiv BO-501-2.

The indicated data are not to be considered as specification.

Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this, liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie
Kennedyplatz 1
D-50569 Cologne, Germany
<http://rch.lanxess.com>