

LEVANYL®
Orange GR-HS-LF

Colour Index	Part I Pigment Orange 34
	Part II 21115
Composition	aqueous, solvent free, organic pigment preparation
Safety data sheet	138235
Form supplied	free-flowing paste suitable for pumping and metering
Shade tolerance (CIElab)	DE max. 1.0 (shade changes to reddish and dead after storage)
Color strength tolerance	95.0 – 105.0%
Density (23 °C)	1.05 – 1.45 g/cm ³
Main fields of application	Paints & Coatings, Wood protection
Storage stability	24 months from delivery ex plant LANXESS Deutschland GmbH
Pigment content	approx. 38 %
Dispersing agent	nonionic
pH-Value	6.0 – 8.0 form supplied (according to DIN ISO 787-9)
Viskosity (23 °C)	max. 1000 mPa s (D = 70 s ⁻¹ , DIN 53019)

Notes on processing:

Always stir before use and close containers after use.

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie Additives
Kennedyplatz 1
50569 Cologne, Germany
<http://rch.lanxess.com>