


BAYSCRIPT® Yellow GGN liq.

General properties	Highly purified, very low salt grade yellow dye Excellent filtration properties (0.45 µm) Very good lightfastness Excellent match for green shade yellow ink-jet inks
Color Index Part I	D. Y. 132
Color Index Part II	–
Chemical class	Disazo dye
Appearance	Yellow liquid
Dye content	≈ 10%
Color strength tolerance	± 5%
Solvent	Water
Surface tension	> 50 mN/m
pH (form supplied)	7 – 9
Viscosity	< 10 mPas
Filterability (0.45 µm filter)	≤ 0.01% residue
Lightfastness	3 – 4
Solubility (g/L at 25 °C)	Water____miscible Glycols____miscible
Ion content (ppm)	Chloride < 50 Sulfate < 50 Calcium < 30 Magnesium < 20 Silicon < 20 Iron < 20
Applications	Water-based inks Thermal and piezo ink-jet printing Office supplies Fine liner inks Writing instruments (felt-tip markers, fiber-tip pens, extruded plastic pens)
Stability	Storage stability: 12 months from delivery ex plant. Protect from freezing. BAYSCRIPT® Yellow GGN liq. is stable against weak acids and bases.

Absorbance curve

Yellow GGN liq. in water



This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie Additives
Kennedyplatz 1
50569 Cologne, Germany
<http://rch.lanxess.com>