

Rhenodiv® DALE 667

Release agents

Function

Internal release agent for uncured rubber compounds

Product description

Composition:	combination of fatty acids and synthetic waxes
Appearance:	white-yellow pellets
Evaporation loss (2 h, 105°C):	< 1%
Iodine Number:	approx. 2
Ester Number:	approx. 5
Physiological properties:	see safety data sheet

Use

Mode of action:	Rhenodiv DALE 667 acts as an internal release agent. It lowers the viscosity of the rubber compound and exhibits a tendency to migrate to the surface of the uncured rubber compound.
Processing:	Rhenodiv DALE 667 is added to the rubber mixture during the first mixing stage.
Dosage:	1-3 phr
Application:	Uncured rubber compounds

Packing

25 kg paper bags on 1,000 kg skids

Storage stability

In original closed containers under cool and dry conditions 24 months from date of production

Handling

Please consult material safety data sheet (MSDS) for additional handling information on Rhenodiv DALE 667.

The indicated data are not to be considered as specifications.

Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this, liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie
Kennedyplatz 1
D-50569 Cologne, Germany
<http://rch.lanxess.com>