

Rhenocure® HX

Specialty and standard chemicals

Function

Mainly used as a secondary accelerator in compounds based on NR, IR, BR, SBR, and NBR

Product description

Composition:	Cyclohexylethylamine
Appearance:	colorless to pale yellowish liquid
Density, 20 °C:	approx. 0.85 g/cm ³
Boiling point:	approx 165 °C
Physiological properties:	see safety data sheet

Use

Mode of action:	Rhenocure HX is a mild accelerator, which is mainly used as a secondary accelerator. Rhenocure HX is used in compounds containing dithiocarbamates, especially ZEPC. It is also used in conjunction with Rhenofit 3555 to activate silica fillers.
Processing:	Rhenocure HX is easy to incorporate and the dispersion achieved is highly satisfactory.
Dosage:	0.5-3.0 phr
Application:	Dipped goods, fabric proofings, sheetings

Packaging

20 kg metal drums on 280 kg skid

Storage stability

In original closed drums under cool and dry conditions 730 days from date of production

Handling

For additional handling information on Rhenocure HX please consult current safety data sheet.

Our technical advice - whether verbal, in writing or by way of trials - is given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. It does not release you from the obligation to test the products supplied by us as to their suitability for the intended processes and uses. The application, use and processing of the products are beyond our control and, therefore, entirely your own responsibility. Should, in spite of this, liability be established for any damage, it will be limited to the value of the goods delivered by us and used by you. We will, of course, provide products of consistent quality within the scope of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie
Kennedyplatz 1
D-50569 Cologne, Germany
<http://rch.lanxess.com>