

SOLFORT® Red BBW-AL 01

Colour Index	Part I Part II	Pigment Red 112 12370
Chemical description	Azo pigment	
Safety data sheet	5166519	
Form supplied	powder	
Density (23 °C)	approx. 1.3 g/cm ³ (according to DIN ISO 787-10)	
Main fields of application	Seed treatment	
Storage stability	60 months from delivery ex plant LANXESS Deutschland GmbH	
Water content	< 1%	
pH-Value (10% in water)	6 - 8,5 (according to DIN ISO 787-9)	
Conductivity (23 °C)	< 200 µS/cm	

This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie Additives
Kennedyplatz 1
50569 Cologne, Germany
<http://rch.lanxess.com>

