

LEVANOX® Yellow 3910 LF

Colour Index	Part I Pigment Yellow 42 Part II 77492
Composition	aqueous, solvent free, inorganic pigment preparation
Safety data sheet	154028
Form supplied	paste – like pumpable dispersion
Shade tolerance (CIELab)*	DE max 1.0 95.0 – 105.0%
Color strength tolerance	1.66 – 1.84 g/cm ³
Density (23°C)	Emulsion paints
Main fields of application	phenolic resin, melamine resin, abrasive paper, synthetic leather (coagulation), technical laminate paper, paper pulp, paper coating, wallpaper colors, nonwoven, wood stains, asphalt, seed, fertilizers, shoe polishes, detergents and cleansing
Further applications	
Storage stability	24 months from production at LANXESS Deutschland GmbH
Pigment content	approx. 57 %
Dispersing agent	nonionic
pH value	6.0 – 8.0; 10% in KCl solution (according to DIN ISO 787-9)
Viscosity (23 °C)	max. 3500 mPa s (D = 29 s ⁻¹ , DIN 53019)

Notes on processing

Always stir before use and close containers after use.



This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



LANXESS Deutschland GmbH
Business Unit Rhein Chemie Additives
Kennedyplatz 1
50569 Cologne, Germany
<http://rch.lanxess.com>

