

## LEVANOX® Red 130 LF 01

<b>Colour Index</b>	Part I Pigment Red 101 Part II 77491
<b>Composition</b>	aqueous, solvent free, anorganic pigment preparation
<b>Safety data sheet</b>	57260137
<b>Form supplied</b>	paste – like pumpable dispersion
<b>Shade tolerance (CIELab)</b>	DE max 1.0
<b>Color strength tolerance</b>	95.0 – 105.0%
<b>Density (23°C)</b>	1.90 – 2.10 g/cm <sup>3</sup>
<b>Main fields of application</b>	emulsion paints, technical laminate paper
<b>Further applications</b>	phenolic resin, melamine resin, abrasive paper, synthetic leather (coagulation), paper pulp, paper coating, wallpaper colors, nonwoven, wood stains, asphalt, seed, fertilizers, shoe polishes, detergents and cleansing agents
<b>Storage stability</b>	24 months from delivery ex plant LANXESS Deutschland GmbH
<b>Pigment content</b>	approx. 63 %
<b>Dispersing agent</b>	nonionic
<b>pH value</b>	6.0 – 8.0, 10% in KCl solution (according to DIN ISO 787-9)
<b>Viscosity (23 °C)</b>	max. 3000 mPa s (D = 29 s <sup>-1</sup> , DIN 53019)

### Notes on processing

Always stir before use and close containers after use.



This information and our technical advice - whether verbal, in writing or by way of trials - are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided - especially that contained in our safety data and technical information sheets - and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility. Our products are sold in accordance with the current version of our General Conditions of Sale and Delivery.



**LANXESS Deutschland GmbH**  
Business Unit Rhein Chemie Additives  
Kennedyplatz 1  
50569 Cologne, Germany  
<http://rch.lanxess.com>

